

# TECHNICAL DATASHEET

## **MILLIFOAM APS200GR**

MILLIFOAM® APS200GR is a closed-cell, 100% recyclable thermoplastic polyethyleneterephthalat (PET) structural foam core. The foam grade offers new perspectives towards sustainable composite products and is steadily substituting core materials such as Balsa, SAN or PVC.

Polymer	rPET (100% rec.)	Sheet Size	2440 x 500 mm
Thickness range	1.0-5.0 mm	Supplier	Armacell

MILLIFOAM® APS200GR has a high temperature resistance up to 150°C (300°F), which leads to shorter cycle times, increased productivity and better mechanical properties in the laminate. The foam is compatible with all common resin systems and lamination processes like infusion or prepreg. Its thermoformability provides tremendous manufacturing advantages and makes it easy to shape by machining. MILLIFOAM® APS200GR can be used in wind energy, rail and road transport, marine or building and construction.

### Properties

Density	200 kg/m <sup>3</sup>
Compressive Strength	4.0 MPa
Compressive Modulus	230 MPa
Tensile Strength	3.9 MPa
Tensile Modulus	235 MPa
Shear Strength	1.75 MPa
Shear Modulus	51 MPa
Thermal Conductivity at 23°C	0.043 W/mK
Thermoforming Temperature	155-190°C (311-374°F)

### Disclaimer

MILLIFOAM® is a registered trademark of 4a manufacturing GmbH. We have taken great care in preparing the presented data and technical advice. However, the data is based on vendor information and no warranty is made, either expressed or implied, regarding its accuracy or the results to be obtained from the use of such information.



**4a manufacturing GmbH**  
Industriepark 1 // A-8772 Traboch  
office@4a-manufacturing.at // +43 664 80106-600

[www.4a-manufacturing.at](http://www.4a-manufacturing.at)