

# TECHNICAL DATASHEET

## **MILLIFOAM DIV130F**

MILLIFOAM® DIV130F is a closed-cell, rigid polymer foam based on polyether sulfone (PESU) chemistry. It offers excellent fire, smoke and toxicity (FST) properties and good mechanical and processing characteristics. It is the material of choice for structures, radomes and interior design and additionally meets the US and European regulatory requirements for commercial aircraft interiors.

Polymer	PESU	Sheet Size	2380 x 580 mm
Thickness range	1.0-3.0 mm	Supplier	Diab Group

MILLIFOAM® DIV130F is compatible with most common aerospace composite processes including vacuum bag processing and matched tooling and press processing with temperatures up to 220°C (428°F). It fulfils exceptional fatigue life, good chemical resistance and excellent heat ageing at 180°C (356°F). As core material in sandwich structures it is hot and cold formable and is fast and easy to process. The thermoforming process window depends on geometry, applied stretching, thermoforming method and sheet thickness. Up to 200°C the foam is rather robust.

Properties	
Density	130 kg/m <sup>3</sup>
Compressive Strength	1.7 MPa
Compressive Modulus	60 MPa
Tensile Strength	3.3 MPa
Shear Strength	1.7 MPa
Shear Modulus	30 MPa
Dielectric constant @ 10GHz	1.17
Loss tangent @ 10 GHz	0.0070
Coefficient of Thermal Expansion	2.0 1/K*10E-5
Thermoforming Temperature	205-230°C (401-446°F)

### Disclaimer

MILLIFOAM® is a registered trademark of 4a manufacturing GmbH. We have taken great care in preparing the presented data and technical advice. However, the data is based on vendor information and no warranty is made, either expressed or implied, regarding its accuracy or the results to be obtained from the use of such information.



**4a manufacturing GmbH**  
Industriepark 1 // A-8772 Traboch  
office@4a-manufacturing.at // +43 664 80106-600  
[www.4a-manufacturing.at](http://www.4a-manufacturing.at)