

TECHNICAL DATASHEET

MILLIFOAM DIV60H

MILLIFOAM® DIV60H is a closed-cell, rigid polymer foam based on polyvinylchloride (PVC) chemistry. It offers excellent mechanical properties to low weight and is ideal for applications subjected to fatigue, slamming or impact loads. With its excellent mechanical properties to weight, it is the foam of choice for marine, land transportation, wind energy, civil infrastructure and general industrial markets.

Polymer	PVC	Sheet Size	2440 x 610 mm
Thickness range	1.0-4.0 mm	Supplier	Diab Group

MILLIFOAM® DIV60H is compatible with all commonly used resin and manufacturing systems with a maximum processing temperature of 90 °C. The foam has an excellent chemical resistance, low water absorption and good thermal/acoustic insulation properties including a consistent high-quality surface structure. It has a low resin uptake and is fast and easy to process and therefore an all-purpose material for the use in multiple industries.

Properties

Density	60 kg/m ³
Compressive Strength	0.9 MPa
Compressive Modulus	70 MPa
Tensile Strength	1.8 MPa
Tensile Modulus	75 MPa
Shear Strength	0.76 MPa
Shear Modulus	20 MPa
Coefficient of Thermal Expansion	4.0 1/K*10E-5
Thermoforming Temperature	90-120°C (194-248°F)

Disclaimer

MILLIFOAM® is a registered trademark of 4a manufacturing GmbH. We have taken great care in preparing the presented data and technical advice. However, the data is based on vendor information and no warranty is made, either expressed or implied, regarding its accuracy or the results to be obtained from the use of such information.



v1.0

4a manufacturing GmbH
Industriepark 1 // A-8772 Traboch
rfq.man@4a.at // +43 664 80106-600

www.millifoam.at