

# TECHNICAL DATASHEET



## MILLIFOAM KER100GR

MILLIFOAM® KER100GR is a closed-cell, rigid polymer foam based on polyethylenterephthalat (PET) chemistry. It is the foam of choice for structural core materials with stable properties and improved resin uptake performance. It allows to comply with the wind energy aim to reduce footprint and reinforce overall goals of waste reduction.

Polymer	PET	Sheet Size	2440 x 500 mm
Thickness range	1.0-5.0 mm	Supplier	Gurit

MILLIFOAM® KER100GR is compatible with a wide range of resin systems including epoxy, vinyl ester, unsaturated polyester and phenolic resins. It can be processed at high temperatures, withstanding high exotherms and offers outstanding chemical resistance and good adhesion. Applicable processing techniques include vacuum infusion, bonding, prepreg, and thermoforming. As highly consistent foam, it is ideal for wind energy, marine, industrial, and transportation applications.

### Properties

Density	100 kg/m <sup>3</sup>
Compressive Strength	1.30 MPa
Compressive Modulus	91 MPa
Tensile Strength	1.82 MPa
Shear Strength	0.80 MPa
Shear Modulus	25 MPa
Thermoforming Temperature	140-160°C (284-320°F)

### Disclaimer

MILLIFOAM® is a registered trademark of 4a manufacturing GmbH. We have taken great care in preparing the presented data and technical advice. However, the data is based on vendor information and no warranty is made, either expressed or implied, regarding its accuracy or the results to be obtained from the use of such information.



v1.0

4a manufacturing GmbH  
Industriepark 1 // A-8772 Traboch  
rfq.man@4a.at // +43 664 80106-600

[www.millifoam.at](http://www.millifoam.at)