

TECHNICAL DATASHEET

MILLIFOAM RHC71HF

MILLIFOAM® RHC71HF is a closed-cell rigid foam based on polymethacrylimide (PMI) chemistry and contains no CFC's. With its extremely low dielectric constant and particularly favorable transmission properties in the high frequency region, it is ideal for the use in antenna systems. Applications range from miniature antennas in cell phones to large fixed ship-based and stationary antenna structures, radomes and mammography plates.

Polymer	PMI	Sheet Size	2500 x 625 mm
Thickness range	0.5-3.0 mm	Supplier	Evonik GmbH

Featuring an extremely fine cell structure, the foam ensures minimal resin uptake and good compatibility with metallic facing materials due to the absence of corrosive effects. MILLIFOAM® RHC71HF is suitable for hand lay-up, pre-preg processing and vacuum infusion at temperatures up to 130°C (266°F) and pressures up to 0.3 MPa (44 psi). The foam can be easily thermoformed or CNC machined to meet customized application requirements.

Properties

Density	75 kg/m ³
Compressive Strength	1.5 MPa
Tensile Strength	2.8 MPa
Tensile Modulus	92 MPa
Shear Strength	1.3 MPa
Shear Modulus	29 MPa
Coefficient of Thermal Expansion	3.23 1/K*10E-5
Dielectric Constant @10GHz	1.093
Loss Tangent @10GHz	0.0038
Thermoforming Temperature	195°C (383°F)
Drying Conditions	4 hrs @ 130°C ± 5°C (266°F ± 9°F)

Disclaimer

MILLIFOAM® is a registered trademark of 4a manufacturing GmbH. We have taken great care in preparing the presented data and technical advice. However, the data is based on vendor information and no warranty is made, either expressed or implied, regarding its accuracy or the results to be obtained from the use of such information.



4a manufacturing GmbH
Industriepark 1 // A-8772 Traboch
office@4a-manufacturing.at // +43 664 80106-600
www.4a-manufacturing.at