

TECHNICAL DATASHEET

MILLIFOAM RHC71IGF

MILLIFOAM® RHC71IGF is a closed-cell rigid foam based on polymethacrylimide (PMI) chemistry and contains no CFC's. It is the structural foam of choice for a broad range of automotive, electronics, medical and other industrial applications. In the medical market, it is a commonly used core material for x- ray and CT tabletops.

Polymer	PMI	Sheet Size	2500 x 625 mm
Thickness range	0.5-3.0 mm	Supplier	Evonik GmbH

Less resin uptake during part processing means lower final part weight and reduced overall cost. MILLIFOAM® RHC71IGF is suitable for prepreg processing, resin infusion and RTM process up to temperatures of 130°C (266°F) and pressures of 0.3 MPa (44 psi). Its thermoformability provides tremendous manufacturing advantages and makes it easy to shape by machining.

Properties

Density	75 kg/m ³
Compressive Strength	1.5 MPa
Compressive Modulus	73 MPa
Tensile Strength	2.8 MPa
Tensile Modulus	92 MPa
Shear Strength	1.3 MPa
Shear Modulus	29 MPa
Coefficient of Thermal Expansion	3.81 1/K*10E-5
Thermoforming Temperature	195°C (383°F)
Drying Conditions	4 hrs @ 130°C ± 5°C (266°F ± 9°F)

Disclaimer

MILLIFOAM® is a registered trademark of 4a manufacturing GmbH. We have taken great care in preparing the presented data and technical advice. However, the data is based on vendor information and no warranty is made, either expressed or implied, regarding its accuracy or the results to be obtained from the use of such information.



4a manufacturing GmbH
Industriepark 1 // A-8772 Traboch
office@4a-manufacturing.at // +43 664 80106-600
www.4a-manufacturing.at